

Grammatura Substance	ISO 536	g/m ²	89	104	118	148	170	216	270	300	350
Spessore Caliper	ISO 534	μm	81	92	101	130	155	216	270	300	350
Volume specifico Bulk	ISO 534	cm ³ /g	0.91	0.88	0.86	0.88	0.91	1	1	1	1
Liscio Bekk Smoothness Bekk	ISO 5627	s	280	280	280	280	280	350	350	300	300
Lucido Gardner Gloss Gardner	ISO 8254-1	%	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max
Bianco ISO Brightness ISO	ISO 2470 (D65)	%	98	98	98	98	98	98	98	98	98
Opacità Opacity ISO	ISO 2471	%	92	95	96	97.5	98	98 min	98 min	98 min	98 min

 Finitura *Finishing*

Silk

 Tipo di stampa *Printing methods*

 Offset in foglio *Sheet-fed offset*

 Applicazioni *End uses*

 Bilanci, Cataloghi, Copertine di libri, Copertine di riviste, Direct Mailing, Inserti, Libri d'arte, Libri di pregio, Opuscoli commerciali, Periodici, Riviste di alta qualità, Riviste di pregio, Stampe commerciali
Business forms, Catalogues, Books covers, Magazine covers, Direct Mailing, Inserts, Art books, Luxury books, Flyers, Magazines, High quality magazines, Luxury magazines, Commercial printing

I valori relativi ai singoli prodotti sono forniti a titolo esemplificativo e possono essere soggetti a modifiche senza preavviso. Ogni valore è soggetto a determinate tolleranze.
 Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.