

Grammatura Substance	ISO 536	g/m <sup>2</sup>	89	104	118	148	170	216	270	300	350
Spessore Caliper	ISO 534	μm	81	92	101	130	155	216	270	300	350
Volume specifico Bulk	ISO 534	cm <sup>3</sup> /g	0.91	0.88	0.86	0.88	0.91	1	1	1	1
Liscio Bekk Smoothness Bekk	ISO 5627	s	280	280	280	280	280	350	350	300	300
Lucido Gardner Gloss Gardner	ISO 8254-1	%	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max	40 max
Bianco ISO Brightness ISO	ISO 2470 (D65)	%	98	98	98	98	98	98	98	98	98
Opacità Opacity ISO	ISO 2471	%	92	95	96	97.5	98	98 min	98 min	98 min	98 min

 Finitura *Finishing*

Silk

 Tipo di stampa *Printing methods*

 Offset in foglio *Sheet-fed offset*

 Applicazioni *End uses*

Bilanci, Cataloghi, Copertine di libri, Copertine di riviste, Direct Mailing, Inserti, Libri d'arte, Libri di pregio, Opuscoli commerciali, Periodici, Riviste di alta qualità, Riviste di pregio, Stampe commerciali

*Business forms, Catalogues, Books covers, Magazine covers, Direct Mailing, Inserts, Art books, Luxury books, Flyers, Magazines, High quality magazines, Luxury magazines, Commercial printing*

I valori relativi ai singoli prodotti sono forniti a titolo esemplificativo e possono essere soggetti a modifiche senza preavviso. Ogni valore è soggetto a determinate tolleranze.  
 Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.